

# ANATASE P101

## Titanium Dioxide Anatase

**Technical Specifications:** (Standard: Q/SNBJ1-2012)

Property	P101
Active TiO <sub>2</sub> %	98 min
Whiteness (As Standard sample)	92 min
Tint Reducing (As Standard sample)	95 min
Volatile at 105°C %	0.5 max
Water absorption	0.5 max
PH value	6.0-8.5
Residue (45um)%	0.5 max
Oil Absorption g/100g	24 max
Isopropoxy titanium triisostearate	1.5 % - 2.5 %

### Application:

Can be used in indoor water based decorative paints, ceiling paints, soap, rubber, paper, leather and ceramic.

### Using Amount:

Using amount depends on application.

### Packing:

25 Kg paper bags.

### Storage:

Store in cool, dry and well ventilated place. Avoid contact with direct sunshine. Shelf life is 2 years in suitable storage conditions.

### Safety:

Please refer to the Safety Data Sheet (SDS) for complete safety information.

No. 1118 Yufan East Road, Zhenhai District Ningbo, China

Mobile: +86 18958278205 Office Phone: +86 57487802965  
Fax: +86 57486365911 Mail: sales@dxchem.com.cn Web: dxchem.com.cn