

# DXPOL N7

## Redispersible Powder Polymer

### Technical Specifications:

Appearance	White powder
Chemical composition	VA / Acrylic Copolymer
Stabilizing System	PVOH
Residual Humidity (%)	Max. 1.5
Bulk Density (g/l)	400 - 600
Ash Content (%)	14 ± 2
Alkali Resistance	High
<u>After 1:1 Dispersion with Water</u>	
MFFT (°C)	0 ± 1
pH (diluted 1-1 in water)	6 - 7

### Application:

REPOL N7 can be used in mortar formulations where good flexibility/elasticity, recovery and thixotropic behavior is required.

### Using Amount:

Usage level depends on application.

### Packing:

Pallet with 18 paper bags, each 25 kg, also 500 or 1000 kg of big bags.

### Storage:

Packages must be stored in a dry and cool warehouse. Pallets must not be stacked on top of each other to avoid caking due to the thermoplasticity of the polymer. Packing must be closed well after usage for protection against humidity and caking. It has to be used within 9 months.

### Safety:

Please refer to the Safety Data Sheet (SDS) for complete safety information.

No. 1118 Yufan East Road, Zhenhai District Ningbo, China

Mobile: +86 18958278205 Office Phone: +86 57487802965  
 Fax: +86 57486365911 Mail: sales@dxchem.com.cn Web: dxchem.com.cn