

CELLOVIS 30 H

HEC (Hydroxyethyl Cellulose)

Technical Specifications:

Physical form	White or yellowish powder
Moisture	5% Max
Degree of substitution	1.8 – 2.5
pH	5.0 – 8.0
Typical Brookfield LVT	
Viscosity @ 1% solution 25°C	1500-2500 cps
Typical Brookfield LVT	
Viscosity @ 2% solution 25°C	24000-36000 cps
Particle Size	Min. 98%@ pass through 100 mesh

Application:

Cellovis 30 H (Enzyme resistant type product) is medium viscosity hydroxyl ethyl cellulose ethers designed for use in a wide range of paint & coating applications. Easily dispersible in cold water.

Using Amount:

Usage level depends on application.

Packing:

25 kg paper bags with PE inner. 20'FCL:14MT with pallets or 16MT without pallets.

Storage:

3 years under cool, dry conditions in original packaging away from heat sources. It is recommended to use the product in rotation on a first-in first-out basis.

Safety:

Please refer to the Safety Data Sheet (SDS) for complete safety information.