

FEOXING

Iron Oxide Black 750

Technical Specifications:

Full shade	∑ E*ab	≤ 1.0
Tinting Strength	%	100±5
Oil Absorption	ml/100g	15 - 25
PH Value		5.0-8.0
Moisture and Volatile Matter at 105°C	max,%	1.0
320 μ Residue on Sieve	max,%	0.4
Matter Soluble in water	max,%	0.5
Tamped Density	g/cm ³	0.8-1.2
Iron oxide Fe ₂ O ₃	min, %	95

Packing:

In 25 kg paper bag/600kg bulk bag then palletized.

Storage:

Protect against weathering/Store in a dry place.

Safety:

The product is not classified as hazardous.